

04

AGRICULTURA Y MEDIO AMBIENTE

Agriculture and environment • Agriculture et environnement • Landwirtschaft und Umwelt

INDUSTRIAL
SEDÓ

Desde 1889



OIL BOOM




















OIL BOOM

OIL BOOM

BLEND

FLEX

| | Método • Test method Méthodes • Methode | Unidades • Units Unités • Einheiten | Nominal • Target Nominal • Wert | Nominal • Target Nominal • Wert | Nominal • Target Nominal • Wert |
|---|---|---|---|--|--|
| Características generales • General features | | | | | |
|  Gramaje Weight • Poids • Flächengewicht | EN - ISO - 2286-2 | g/m ² | 800 | 930 | 1450 |
|  Espesor Thickness • Grosseur • Dicke | EN - ISO - 2286-3 | mm | 0,67 | 0,80 | 1,25 |
|  Acabado Finish • Finition • Endausrüstung | Mate - No lacado • Matt - Not lacquered Mate - Non laqué • Matt - Nicht lackiert | | | | |
|  Longitud del rollo Length • Longueur • Länge | | m | 25 | 25 | 25,5 |
| Composición • Composition | | | | | |
|  Tejido base Base fabric • Tissue de base • Grundstoff | | | 100% PES HT | 100% PES HT | 100% PES HT |
|  Hilos Yarn count • Fil • Garn | | | 1100 dtex | 1100 dtex | 1670 dtex |
|  Tipo de recubrimiento Type of coating • Type d'enduction • Beschichtungsart | | | PVC | PVC | PVC |
| Características técnicas • Technical features | | | | | |
|  Resistencia tracción Tensile strenght Résistance rupture Reißfestigkeit | URDIMBRE • WARP CHAÎNE • KETTE TRAMA • WEFT TRAME • SCHUSS | EN - ISO - 1421 | daN/5cm | 300 280 | 400 380 600 |
|  Resistencia desgarre Tear strenght Résistance Déchirure Weiterreißfestigkeit | URDIMBRE • WARP CHAÎNE • KETTE TRAMA • WEFT TRAME • SCHUSS | DIN - 53363 | da/N | 40 40 | 60 50 175 175 |
|  Adherencia 23°C Adhesion • Adhérence • Haftung | | EN - ISO - 2411 | daN/5cm | 10 | 12 12 |
|  Temperaturas extremas de trabajo Working extrem temperatures Températures extrêmes d'utilisation Temperaturbeständigkeit | | EN - 1876-1 | °C | -30 / +70 | -30 / +70 -30 / +70 |
|  Resistencia frente al SAE-30 24h 80°C Resistance to SAE-30 24h 80°C Résistance au SAE-30 24h 80°C Widerstand gegen SAE-30 24h 80°C | | Método Interno Internal method Méthode interne Eigener methode | % Pérdida de peso % Weight loss % Perte de poids % Gewicht-verlust | 3,5 | 1,5 3 |
|  Resistencia frente al Gasoil 24h 80°C Resistance to Diesel 24h 80°C Résistance au Diesel 24h 80°C Ölbeständigkeit 24h 80°C | | Método Interno Internal method Méthode interne Eigener methode | % Pérdida de peso % Weight loss % Perte de poids % Gewicht-verlust | 15 | 4,5 6 |
|  Resistencia frente a la Gasolina 3h 25°C Resistance to Petrol 3h 25°C Résistance à l'Essence 3h 25°C Beständigkeit gegen Benzin 3h 25°C | | Método Interno Internal method Méthode interne Eigener methode | % Pérdida de peso % Weight loss % Perte de poids % Gewicht-verlust | 15 | 2,5 5 |
|  Resistencia al pliegue Fold test Résistance au pliage Knickfestigkeit | | Método Interno Internal method Méthode interne Eigener methode | > 100.000 Ciclos • Cycles Cycles • Zyclus | Sin grietas No cracking Sans fissures Keine misse | Sin grietas No cracking Sans fissures Keine misse Sin grietas No cracking Sans fissures Keine misse |
|  Solidez a la luz Lightfastness • Résistance à la lumière • Lichtechtheit | | EN - ISO - 105-B02 | 360h | 6 | 6 6 |
|  Tratamiento antifúngico Antifungal treatment • Traitement anti-moisissures Fungizid Ausgerüstet | | | | ✓ | ✓ ✓ |

La información facilitada corresponde a valores promedio de un producto recién fabricado con un rango de tolerancia de +/- 10 %, se facilita como indicación y guía solamente, sin ninguna vinculación jurídica. Los valores proporcionados se refieren al estado original de la mercancía enviada antes del procesamiento o elaboración por parte del cliente. Por razones técnicas puede haber ligeras variaciones durante la producción, así como pequeñas alteraciones del color, las referencias al RAL son solo indicativas. El cliente como propietario del diseño debe comprobar la aptitud y compatibilidad del producto para el uso previsto antes de proceder a su procesamiento o elaboración.

The information provided corresponds to average values of a newly manufactured product with a tolerance range of +/- 10% which is provided as an indication and guidance only, without any legal binding. The values provided refer to the original status of the goods sent before processing or handling by the customer. For technical reasons there may be slight variations during production, as well as slight color alterations, the RAL references are only indicative. The customer as owner of the design must check the aptitude and compatibility of the product for the intended use before proceeding with its processing or production.

La gama OIL BOOM esta diseñada especialmente para la fabricación de elementos que estén en contacto con productos hidrocarburos. Es un producto ideal para la confección de barreras de contención marítimas preventivas o paliativas ante derrames en medios acuáticos. Existen tipologías diferentes con distintos gramajes y características.

The OIL BOOM range has been specially designed for the manufacture of elements that come into contact with hydrocarbons. It is the ideal product for making preventive or palliative maritime containment barriers against oil spills in aquatic environments. There are two different types with different weights and characteristics

OIL BOOM ESTÁNDAR

Colores • Colors • Couleurs • Farben / Ancho • Width • Laize • Breite: ● 218 cm




30C-238*800 g/m² ● M3901

VENTAJAS TÉCNICAS TECHNICAL ADVANTAGES



OPCIONES DE ACABADO FINISHING OPTIONS



Se trata de un tejido muy preparado para realizar las funciones de contención ante derrames de hidrocarburos, de manera estandar se presenta en ancho de 205cm, acabado mate y color naranja 30C-238.

This fabric is very well equipped for containment functions in the event of oil spills. It is supplied as standard in a width of 205 cm with a matt finish in Orange 30C-238.



SERVICIOS

- Troceado de piezas
- Metreado
- Anchos y longitudes ajustables
- Libre de ftalatos
- Colores especiales

SERVICES

- Roll slitting
- Cut Length
- Width and length adjustments
- Phtalate Free
- Special colours

SERVICES

- Tronçonnage en morceaux
- Métrage
- Largeurs et longueurs adaptables
- Sans Phtalates
- Couleurs spéciales

DIENSTLEISTUNGEN


- Schneiden
- Schnittlänge
- Kupon und Breitenschnitt nach Ihren Wünschen
- Phtalat frei
- Sonderfarben

OIL BOOM BLEND

Colores • Colors • Couleurs • Farben / Ancho • Width • Laize • Breite: ▲ 250 cm



30C-238* 930 g/m² ▲ M4888



VENTAJAS TÉCNICAS TECHNICAL ADVANTAGES



OPCIONES DE ACABADO FINISHING OPTIONS



Su principal característica BLEND es la incorporación de **poliuretano PU junto al PVC premium**. Con lo que se aumenta la resistencia a la extracción de hidrocarburos, así como también la resistencia a la abrasión de la lona. De manera estandar se presenta en acabado mate, color naranja 30C-238 y ancho de 250cm.

The main feature of the BLEND fabric is the incorporation of PU polyurethane along with the premium PVC. This increases its resistance to the extraction of hydrocarbons as well as the abrasion resistance of the canvas. It is supplied as standard in a matt finish in Orange 30C-238 in width of 250 cm.



* Consultar disponibilidad o pedido mínimo • Check availability or minimum order



OIL BOOM FLEX

Colores • Colors • Couleurs • Farben / Ancho • Width • Laize • Breite: ▼ 205 cm



30C-238* 1450 g/m² ▼ M5576

Este producto se realiza con un tejido base conformado por hilos de 1.670 dtex. Su composición aporta mayor flexibilidad al tejido. Se presenta de manera estandar con acabado mate, color naranja 30C-238 y ancho de 205cm.

This product is made with a base fabric of 1,670 DTEX yarn. Its composition brings added flexibility to the fabric. It is supplied as standard in a matt finish in Orange 30C-238 and a width of 205 cm.

VENTAJAS TÉCNICAS TECHNICAL ADVANTAGES



OPCIONES DE ACABADO FINISHING OPTIONS



PHthalates FREE
LIBRE DE FTALATOS





+34 977 65 50 07

info@industrialsedo.com

Industrial Sedó, S.L.
Camí Mas Llagostera S/N
43762 La Riera de Gaià
(Tarragona) Spain

www.industrialsedo.com



Este catálogo es una herramienta informativa de nuestros productos, no podrá usarse como herramienta contractual. Es imprescindible que el cliente compruebe las características técnicas y especificaciones de cada producto.

Los datos de garantías están sujetos siempre a la buena conservación y buen uso de los productos. Consulte las particularidades de cada uno de ellos.